

**SPECIFICATION  
KRAFTLINER PM-4**

Property	Values												
	115	120	125	130	135	140	150	160	170	175	186	200	
1. Grammage, g/m <sup>2</sup> (ISO 536)													
2. Moisture, %, (ISO 287), min/max	7 - 9												
3. Cobb test 60, g/m <sup>2</sup> (ISO 535) min/max	25-38 38-52												
4. SCT CD, kN/m (ISO 9895)	2,20	2,3	2,50	2,55	2,60	2,75	2,85	3,00	3,15	3,30	3,55	3,85	
<b>Typical</b>	2,15	2,25	2,40	2,45	2,50	2,55	2,80	2,90	3,00	3,10	3,45	3,75	
<b>Guaranteed min</b>													
5. Burst, kPa, (ISO 2758)	590	600	630	640	650	670	700	740	770	780	820	870	
<b>Typical</b>	580	590	610	620	640	660	690	720	740	755	790	840	
<b>Guaranteed min</b>													
6. Air Resistance (Gurley), s, (ISO 5636/5)	70 60												
<b>Typical</b>	16												
<b>Guaranteed min</b>	16												
7. Dennison test, №, (TAPPI 459-SU-65)	16												
<b>top min</b>	16												
8. Test climate, (ISO 187)	Temperature (23 ± 1) °C, relative humidity (50 ± 2) %												
	Maximum basic weight tolerance ± 3 %.												