

**Technical specification**  
**Wet strength packaging paper**  
**Public joint-stock company**  
**«Troitskaya paper mill»**  
**Grade VPM SK**  
**TU 5435-004-00278971-2007**

**August 2018**

Parameter	Measurement methodology	30 g/m <sup>2</sup>
1. Paper weight per 1 m <sup>2</sup> , g	GOST 13199	30.0 + 2.0
2. Breaking force, in the transverse direction, N, minimum	GOST ISO 1924-1	12
3. Relative burst strength, kPa, minimum	GOST 13525.8	350
4. Relative wet strength, %, minimum:	Clause 4.2 of this TU	12.0
5. Smoothness (the side with higher value), s, minimum	GOST 12795 (ISO 5627)	400
6. Surface water absorptiveness at one-sided wetting, Cobb 60, g/m <sup>2</sup> , maximum	Clause 4.3 of this TU	25.0
7. Moisture, %	GOST 13525.19 (ISO 287)	5.5-7.5
8. Whiteness, % minimum: - no optical bleaching agent - with optical bleaching agent	Clause 4.4 of this TU	80.0 90.0

L. Beresina  
Head of process technology

E. Butoragina  
Acting head of QCD and L