



GAMA IMPEKS FOOD

Bleached kraft paper(60-90 gsm)

Наименование показателей Property		60	70	80	90	Метод испытания
Basis weight		60 ±2,5	70 ±2,5	80 ±3	90 ±4	По ГОСТ 13199 (ISO 536)
Tensile strength	MD	6,0	6,5	7,2	7,4	ISO 1924-1
	CD	2,5	2,7	3,1	3,6	
Stretch, %	MD	1,4	1,7	1,9	1,7	
	CD	3,8	3,6	3,3	3,6	
Bursting strength, kPa		230	220	220	255	
Breaking length, m	MD	9500	9320	9270	8800	
	CD	4300	4200	4100	3900	
Tearing strength, N	MD	82	97	107	110	По ГОСТ 13525.3 (ISO 1974)
	CD	35	40	45	50	
(Cobb60) not more Reverse side Top side	WS	22	22	22	22	По ГОСТ 12605 (ISO 535)
		26	26	26	26	
Thickness, μm		79	85	106	112	
Roughness, ml/m Reverse side Top side		210		485	330	
		159		280	300	
Brightness, not less		93,9	93,5	93	104,8	По ГОСТ 30113
Brightness CIE		112,9	100	112	136,6	
Влажность, % Moisture		5+1/- 1.5	5+1/- 1.5	5+1/- 1.5	5+1/- 1.5	По ГОСТ 13525.19 (ISO 287)