

Kraft Sack Paper
Technical specification

Substance, gsm	70 \pm 2 gsm
Relative Elongation, CD % not less	4.5
Breaking Load , CD, kN/s, not less than	3.7
Tear resistance, Hm, not less than	60
Surface absorption (Cobb), MD, not less	30
Mosture %	7 \pm 1

Kraft sack paper

Substance, gsm	80 ± 2.0
Relative Elongation, CD % not less	4.7
Breaking Load , CD, kH\s, not less than	3.8
Tear resistance, H\m, not less than	65
Surface absorption (Cobb), MD, not less	30
Mosture %	7-9

Kraft Sack Paper

Technical specification

Substance, gsm	90 \pm 3 gsm
Relative Elongation, CD % not less	5.0
Breaking Load , CD, kN/s, not less than	3.9
Absolute Tear Resistance, H/m, not less than	70
Surface absorption (Cobb), MD, not less	30
Mosture %	8