



# GAMA IMPEKS FOOD

## Unbleached sulphate softwood pulp

TU 5411-098-00279410-2007

### Specifications

Parameter	Value <u>TU 5411-098-00279410-2007</u> statutory document name
1. Kappa number	21-30
2. Mechanical strength when ground in a pulp fibermaster with a Shopper-Riegler index of up to 60, breaking length, not less	8700
3. Ash content, %, not more	1.0
4. Dirt count in 500 g motes sq mm of weight, pcs., not more: area in light 1.00 mm <sup>2</sup> up to 2.00 mm <sup>2</sup> in light 2.00 mm <sup>2</sup>	1000 not allowed
5. Moisture, %, not more	20
6. Estimated moisture, %	10